TECHNICAL DATA & APPLICATION SHEET



SV36 Petrol Resistant Acrylic Solution

FOR PROFESSIONAL USE ONLY

DESCRIPTION

SV36 – petrol resistant acrylic solution produces a hard, flexible, petrol resistant coating. It has excellent resistance to water, alkalis and commercial grades of petroleum and hydraulic fluids, making this resin ideal for use on areas such as concrete driveways in petrol stations. The product is supplied as a ready to use form at 24% solution.

FEATURES

- Ideally suited for protection of concrete
- Excellent resistance to water
- Excellent resistance to alkalis
- Excellent resistance to petroleum and hydraulic fluids
- Compatible with a wide range of industrial solvents

PERFORMANCE BENEFITS

- Produces a hard, yet flexible clear film
- Excellent resistance to weathering
- Excellent resistance to petrol

TYPICAL PHYSICAL PROPERTIES

Clear colourless liquid	%Nonvolatile:	
	Weight*	23.0-25.0
Solvent type:	Volume*	20.7-22.5
R100 / xylene	Specific Gravity	0.90
	Viscosity Brookfield LVT (sp1/30rpm/25°c	50-100 cps
	Flash point (°c)	24

On-Crete Australia Pty Ltd has no control over the use or storage of this product and therefore does not accept any liability in this regard. Any verbal advice given should not be regarded as authoritative information. This information is subject to change without notice, therefore all applicators should ensure they have current information. This product is intended for the use only of skilled tradesmen and where applicable, statutory licensed tradesmen experienced and trained in the use of this product. This product is warranted to be of uniform quality within the manufacturer's tolerance. This manufacturer has no control over the use or misuse of this product, therefore no warranty rests or implied, is or can be made either as to the effects of such use. The manufacturer's obligations shall be limited to replacing product proving to be defective.

Last Updated: 12 JUNE 2012 Technical Data & Application Sheet SV36 Petrol Resistant Acrylic Solution Page 1 of 1

Phone: 07 5593 6884

Fax: 07 5593 6885